

Mode: Similarity Report

paper text:

Press Tool for the V-Bending Process of Stainless Steel Plate: Designing and Manufacturing Rusdi Nur^{1, 2, a)}, Muhammad Arsyad Suyuti^{1, b)}, Muhammad Iswar^{1, c)}, and Ridwan Jamaluddin^{1, d)} Author Affiliations ¹Mechanical

Engineering Department, Politeknik Negeri Ujung Pandang, Jalan Perintis Kemerdekaan Km. 10

2

Makassar, **90245**, South Sulawesi, **Indonesia** ²**Center for Materials and Manufacturing, Politeknik Negeri Ujung Pandang, Jalan Perintis Kemerdekaan Km. 10** Makassar, **90245**, South Sulawesi, **Indonesia** Author Emails **a) Corresponding author: rusdinur@poliupg.ac.id** **b) muhammadarsyadsuyuti@poliupg.ac.id** **c) muh_iswar@poliupg.ac.id**

^{d)}ridwanjamiludin70@gmail.com Abstract. Stainless steel is a plate material that is widely used in the home and transportation industry. In bending stainless steel plates, a bending tool that has a greater compressive ability is needed. This paper was presented to design and manufacture a press tool and aims to produce a V-bending tool for stainless steel sheets. The punch angle variation used is 80°, 85°, and 90° with the die angle of 90°. While the punch radius variation is 2 mm, 4 mm and 6 mm. The research method was performed in several

stages, i.e., the literature review stage, the design stage, the manufacturing stage, and the

10

tool testing stage. Based on the test results, the best punch angle and radius are close to 90° for stainless steel with a thickness of 2 mm, namely a punch angle of 90° with a punch radius of 2 mm. The press tool has a capacity that is a bending line

length of 60 mm, a bending width of 44 mm, a spring height of 160 mm, a

8

free stroke of

19.5 mm, and an acceptable spring load of 135.39 N.

It can be concluded that punch radius is a significant factor affecting the

1

loading and springback.

INTRODUCTION This document was prepared using the AIP Conference Proceedings template for Microsoft Word. It provides a simple example of a paper and offers guidelines for preparing your article. Here we introduce the paragraph styles for Level 1, Level 2, and Level 3 headings. Please note the following : Nowadays, the

3

process of forming metal plates in the machining industry is growing quite rapidly, especially in the bending process. The bending process is a

plastic deformation process of metal to a linear axis with little or no change in surface area

6

. Sheet plate was formed through pressure punch and die forming. In the process of bending, there is stretching on the axis of

the neutral plane **along the bending area** , which results in **a straight bending line**

1

[1]. The process of forming metal plates is mostly carried out in various manufacturing industries which are triggered by the many uses of mechanical technology in everyday people's lives whose products or components are made of plate metal. Bending is a process carried out to press the metal plate using a punch until a bend is formed according to the die shape. In the bending process, the stress-strain distribution is very important to achieve perfect bending results according to the desired shape. Thus,

when the load is removed, the material tries to take **its original** shape, **and the material** that was **bent**

7

will come back due to stretching. This material behavior is called springback [2]. Several parameters in the bending process that affect the springback results, i.e., punch and die radius, punch and die angle, clearance between punch and die, static and dynamic friction conditions, plate thickness, elastic modulus, and material dimensions. In the manufacturing industry, a press tool is a production tool that is widely used to form metal, including the plate material bending process, namely the press tool. A Press tool is a type of tool used to cut or shape a product or component from sheet metal plates using a press machine as a pressing device that can produce products of uniform quality and in a short time. Previously, a simple press tool for bending V bottoming was made. This simple press tool is equipped with a 90o angle V-shaped die and punch. This tool functions as a V-bending tool for thin metal sheets with a maximum

bending line width of 50 mm. This research uses St 42 steel material. In this tool, there is still a lack of allowance for the bushing that is not standard so that the top plate and bottom plate shake when operating. The bending angle of the plate as a result of bending this tool is generally greater than 90°. This simple press tool is made specifically for laboratory-scale bending V experiment tests [3]. Another research, making press tool bending tool V with an air bending die and bending plate material, namely steel St.37. Air bending is a method of bending in which the workpiece does not touch all parts of the tool (punch and die). Another term for air bending is partial bending or free bending. In this type of bending, the workpiece is only in contact with the two endpoints of the die and one endpoint of the punch. Therefore, the emphasis on the workpiece does not touch the bottom of the die. This press tool has a simple construction and consists of three main sub-assemblies, namely die set, punch and die sub-assemblies. However, the construction of this press tool still has several weaknesses, such as the guidepost component is not precise and the adjustment of the top plate is not standard, so that the precision level of the tool is still lacking. This tool is also a laboratory-scale experimental study tool [4]. The research result above it has not been obtained optimal results, both in terms of construction and precision. Therefore, this paper presents a design development and manufacture of press tools for V-bending on stainless steel. Stainless steel is a plate material that is widely used in the home and transportation industry [5].

METHODOLOGY The schedule for designing and making a press tool is around June until September 2020. The manufacturing of the press tool was performed in the Mechanical of Workshop and Laboratory of the Mechanical Engineering Department, Ujung Pandang State Polytechnic. Designing the Press Tool The design of this press tool is based on concepts and ideas that have gone through the process of surveying and reviewing various kinds of literature. Therefore, the initial design process was performed to design and manufacture this press tool. This concept is also used to manufacture the shot peening machine [6] and polishing machine [7]. The initial design of this straw press tool can be shown in Fig. 1.

FIGURE 1. Design of press tool for V-bending Tools and Materials The press tool can be produced optimally by preparing the

tools and materials are needed. The details of the tools and materials used

9

can be detailed in TABLE 1. TABLE 1. Materials and tools were used. Materials Tools ? Square steel of 60 x 60 mm ? Steel

plate with a thickness of 22 mm ? Carbon steel with a thickness of 30 mm

5

? Shaft steel with a diameter of 30 mm ? Stainless steel plate with a thickness of 1 mm and 2 mm ? Spring press ? Bolt and nut ? Bushing ? Milling machine ? Lathe machine ? Drilling machine ? Grinding machine ? Jig saw machine ? Universal testing machine (UTM) Galdabini

RESULT AND DISCUSSION In this section, the results of manufacturing a press tool

will be described clearly and will be accompanied by a discussion. Results The

4

press tool of V-bending was designed and manufactured as follows in TABLE 2, including parts, tools, and materials, which were used in the manufacturing process. TABLE 2. Manufacturing parts of the press tool for V-Bending Parts Manufacturing Process 1. Top Plate ? Cutting plates using a grinding machine ? Facing uses a milling machine to reach 315 mm x 200 mm in size. ? Drilling a plate with a diameter of 28 mm and 5 mm into the plate. This hole functions as a bushing fixture. ? Making grooves on the plates using a milling machine. ? Making thread with the tap of M8 x 1.0 mm 2. Pillar ? Cutting the material with a size of 260 mm using a jigsaw machine. ? Facing the material from ?25.4 mm to ?23 mm using a lathe machine ? Facing the material from 260 mm to 240 mm in length using a lathe machine. ? Drilling in diameter of ?15 mm for locking the pillar and taping in M16 X 2.0 mm Parts Manufacturing Process 3. Bottom Plate ? Drilling a plate with a diameter of 25 mm into the plate. This hole functions as a bushing fixture. ? Making grooves on the plates using a milling machine. 4. Die gripper ? Facing the material by using a milling machine. ? Making grooves on the plates using a milling machine. ? Drilling 7 mm in diameter to penetrate the plate. This hole serves as a screw fixer for the die clamp 5. Die ? Facing material to size 60 x 60 x 60 mm using a milling machine. ? Making a V groove using a milling machine. 6. Punch gripper ? Making grooves on the plates using a milling machine. ? Drilling a plate with a diameter of 6 mm through the plate. This hole functions as a bolt fastener for the die clamp Parts Manufacturing Process 7. Bushing ? Facing the material using lathe machine to reach the diameter of 29.30 mm. ? Cutting the material to get the length of 21 mm using jigsaw machine. ? Drilling with a diameter of 23 mm. 8. Punch ? Cutting material using a jigsaw. ? Facing material into a size of 60 x 79.04 mm using a milling machine. ? Making a groove in width of 10 mm and depth of 10 mm using milling machine. ? Making a V groove of 85o and a radius of 2o. ? Drilling with a diameter of 6 mm 9. Locker of pillar and plate ? Facing the material in dimension of 168 mm x 17.00 mm using milling machine ? Drilling with diameter of 23 mm. This hole serves as a bushing fitting. After the process of designing and manufacturing press tool has been completed, then the assembly process for all components, both manufactured and purchased, is carried out, as shown in Fig. 2 and Fig. 3. Description: 1. Top Plate 2. Bottom Plate 3. Pillar 4. Punch gripper 5. 6. 7. 8. FIGURE 2. Result of assembling die set of press tool Die gripper Punch Die Bolt M8 9. Mur M8 10. Bushing 11. Locker of pillar and plate 12. Spring 13. Bolt 14. Ring 15. Bolt M10 16. Bolt M8 FIGURE 3. Result of the die set of press tool after design development The next step, the die set bending test, was conducted experiments on several samples of stainless steel plate. The bending results can be seen in Fig. 4. FIGURE 4. Bending result of stainless steel plate Discussion Based on the results of designing and manufacturing the die set for press tool, the die set was testing in Ultimate Tensile Machine (UTM) Galdabini for different loading. Punch radius was used in this experiment, i.e., 2 mm, 4 mm, 6 mm [8]. The result data was obtained and presented in TABLE 3 and Fig. 5. TABLE 3. Loading data in different of punch angles and punch radius for 1 mm and 2 mm of stainless steel plate. Punch Punch Angle Radius Loading (Newton)

Plate thickness of 1 mm	Plate thickness of 2 mm	5
--------------------------------	--------------------------------	----------

Punch Travel Punch Travel 18.5 19 19.5 Average 18.5 19 19.5 Average 2 80 4 6 1110 1150 1250 1030 1060 1050 920 940 950 1170.00 1046.67 936.67 1300 1220 1130 1310 1300 1303.33 1240 1310 1256.67 1130 1200 1153.33 85 2 4 6 1020 1030 1060 1036.67 1240 1290 1290 1273.33 1140 1140 1160 1146.67 1300 1400 1450 1383.33 1050 1070 1070 1063.33 1210 1240 1260 1236.67 90 2 1040 1040 1060 1046.67 1250 1290 1370 1303.33 4 1010 1020 1020 1016.67 1150 1200 1260 1203.33 6 1020 1040 1050 1036.67 1220 1350 1630 1400.00

80 85 90 Bending Force (N) 1600 1400 1000 1200 800 600 400 80 85 90 0 0 2 Punch Radius (mm) (a) 4 6 8 200 0 0 2 4
 Punch Radius (mm) (b) 6 8 FIGURE 5. Loading graphical on punch radius for different of punch angle in thickness of 1 mm (a) and 2 mm (b) Table 1 and Fig. 5 present several things, namely: for a punch angle of 80°, the bending force will decrease with increasing punch radius for both 1 mm and 2 mm thick plates. The punch angle of 85° gives different results, where the load increases at a punch radius of 4 mm and then decrease at a punch radius of 6 mm. On the other hand, at a 90° punch angle, there is a tendency for the load to increase as the punch radius increases. This result is also strengthened by the study presenting that the punch radius affects the load used in the bending process with ANSYS simulation [8] and FEA simulation [9]. Regarding the punch radius, the results of other studies have found that the addition of the punch radius will increase the springback when bending stainless steel plates [10] and iron sheets [11], medium carbon steel [12][13]. Overall, it can be seen that the required load is greater to bend 1 mm and 2 mm.

CONCLUSION Process of designing and manufacturing the die set of press tool was completed and has been performed to bending of stainless steel plates. The results show that the die set of press tool has worked and functioned well to bend the stainless steel plate. From the results of experiments,

it can be concluded that punch radius is a significant factor affecting the

1

loading and springback.

In the air V -die free bending process, the punch radius is the most significant parameter to be considered

1

. **ACKNOWLEDGMENTS** We would like to acknowledge the Ministry of Education and Culture for funding the research (Research Contract Number: B/49/PL10.13/PT.01.05/2021). We also acknowledge the Director and P3M of Politeknik Negeri Ungjung Pandang who provided the opportunity to support in this research program. **REFERENCES** 1. M.A. Suyuti, M. Iswar, and R. Nur, Effect of Punch Parameters on Springback for Mild Carbon Steel in A V-Shape Bending Process, in: IOP Conf. Ser. Mater. Sci. Eng., (2019), pp. 1–6. 2. Ö. Tekaslan, N. Gerger, and U. Şeker, Mater. Des. 29, 1043–1050 (2008). 3. R. Nur, M.A. Suyuti, and M. Iswar, Log. J. Ranc. Bangun Dan Teknol. 19, 38–43 (2019). 4. R. Nur and M.A. Suyuti, J. Ind. Eng. Manag. Res. 1, 9–14 (2020). 5. L. Gardner, Prog. Struct. Eng. Mater. 7, 45–55 (2005). 6. H.P. Nari, M. Sirman, R. Nur, and M.I. Mukhsen, Redesign and Remanufacturing the Shot Peening Machine: Model and Experiment, in: J. Phys. Conf. Ser., (2021), p. 12009. 7. A. Apollo, R. Nur, M.A. Suyuti, and M. Madjid, Development of polishing machine for preparation metallographic specimen with re-manufacturing, in: IOP Conf. Ser. Mater. Sci. Eng., (2020), pp. 1–6. 8. T. Kartik and R. Rajesh, Adv. Nat. Appl. Sci 11, 178–184 (2017). 9. V. Gautam, P. Kumar, and A.S. Deo, Int. J. Mech. Eng. Technol. 3, 517–530 (2012). 10. M.S. Buang, S.A. Abdullah, and J. Saedon, J. Mech. Eng. Sci. 8, 1322–1331 (2015). 11. C.-C. Chen, Mater. Manuf. Process. 29, 461–465 (2014). 12. M.A. Suyuti and R. Nur, The Influence of Punch Angle on the

Spring Back during V-Bending of Medium Carbon Steel, in: Adv. Mater. Res., (2015), pp. 157–160. 13. M.A. Suyuti, M. Iswar, and R. Nur, Effect of punch angle and punch radius on bend angle through air V- bending of sheet metal, in: AIP Conf. Proc., (2019). Where to Find Further Information We warmly invite you to visit our online platform, Scitation, where you can find further help/advice and publishing policies for AIP Conference Proceedings: ? For authors:

<https://aip.scitation.org/apc/authors/preppapers> ? For conference organizers:

<https://aip.scitation.org/apc/organizers/abstracts> Summary: Points to Consider when Preparing Your Paper 1- Articles should use 8.5 x 11 single column template. 2- Use Times New Roman font, the point size will vary by section. 3- DO NOT alter the margins of our templates. They are carefully designed for AIP's production process: Altering them can cause significant delays. Paper size should be 8 ½ x 11 with margins set at: Top – 1 inch, Left – 1 inch, Bottom – 1.18 inch, Right – 1 inch. 4- DO NOT display the title in ALL CAPS (initial cap only) 5- DO NOT include any headers, footers, or page numbers in your document. They will be added to your article PDF by AIP Publishing, so please do not amend this template to add them to your paper. 6- Line spacing should be 1.0 throughout the entire article, no double spacing. 7- Make sure all author affiliation associations are correct. This means author vs. affiliation and author vs. email address. If there is only one affiliation for all authors, association is not needed. Author names should be listed in First name Surname format. 8- Use clear, legible graphics and diagrams. Readers of your paper will be grateful. If they cannot read it, they are unlikely to cite it. 9- DO NOT use copyrighted material without permission. Papers using copyrighted material without appropriate permission and acknowledgment will be excluded from the proceedings. 10- No 1-page papers please. 1-page, abstract-only contributions are not acceptable and will be excluded from the proceedings. 11- Prepare and format references with care. References should be numbered using Arabic numerals followed by a period (.). 12- Embed all fonts into your article PDF. The importance of font embedding is discussed in the section Font Embedding (above). PDFs supplied without embedded fonts are often completely unusable for printing or publication purposes. In such cases, we must return those PDFs to the proceedings editors for font embedding. Failure to embed fonts can cause unnecessary inconvenience to your proceedings editor(s) and publication delays for other authors. Failure to provide a replacement paper in a timely fashion may result in an article being removed from the proceedings. 13- Check your article PDF file! It is not uncommon for errors to appear in PDFs generated from Microsoft Word – corrupted math, figures reflowing, etc. It is essential to very carefully check your article PDF file before sending it to the proceedings editor(s). 14- Avoid large PDF files (10 MB maximum, ideally). For the benefit of your readers, we recommend keeping your article PDF file below 10 MB. This is a recommendation, not a requirement.

sources:

1 49 words / 2% - Internet from 08-Apr-2021 12:00AM
repository.poliupg.ac.id

2 45 words / 2% - Internet from 08-Apr-2021 12:00AM
repository.poliupg.ac.id

3 49 words / 2% - Crossref
[Adawiya Ali Hamzah. "Effect of crack on human femur bone under axial load", AIP Publishing, 2021](#)

-
- 4 12 words / 1% - Internet from 21-Dec-2021 12:00AM
repository.poliupg.ac.id
-
- 5 19 words / 1% - Internet from 06-Mar-2019 12:00AM
pt.scribd.com
-
- 6 15 words / 1% - Crossref
[T Hadi, N S Pamungkas, W Wahjoedi, T Mulyono. "Innovative products of concrete steel bone testing tools in the field of civil engineering building", IOP Conference Series: Materials Science and Engineering, 2021](#)
-
- 7 15 words / 1% - Crossref
[Özgür Tekaslan, Nedim Gerger, Ulvi Şeker. "Determination of spring-back of stainless steel sheet metal in "V" bending dies", Materials & Design, 2008](#)
-
- 8 12 words / 1% - Crossref
[Chun-Chih Kuo, Hao-Lun Huang, Tse-Chang Li, Kai-Lun Fang, Bor-Tsuen Lin. "Optimization of the pulsating curve for servo stamping of rectangular cup", Journal of Manufacturing Processes, 2020](#)
-
- 9 10 words / < 1% match - Internet from 21-Apr-2021 12:00AM
repository.poliupg.ac.id
-
- 10 11 words / < 1% match - Crossref
[T A Faizal, N H Pandjaitan, M I Rau. "Small dam planning as a water sources alternative in Sekaran Village, Bojonegoro Regency, Indonesia", IOP Conference Series: Earth and Environmental Science, 2021](#)
-
- 11 11 words / < 1% match - Internet from 21-Sep-2021 12:00AM
backend.orbit.dtu.dk
-